

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371

65008-031

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR

09/890091

INTERNATIONAL APPLICATION NO.

PCT/GB/00/00191

INTERNATIONAL FILING DATE

24 January 2000 (24.01.00)

PRIORITY DATE CLAIMED

26 January 1999 (26.01.99)

TITLE OF INVENTION

CONSTRUCTION SYSTEM

APPLICANT(S) FOR DO/EO/US

NEWTON, John Reginald

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☐ This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (24) indicated below.
4. ☒ The US has been elected by the expiration of 19 months from the priority date (Article 31).
5. ☒ A copy of the International Application as filed (35 U.S.C. 371 (c) (2))
 - a. ☐ is attached hereto (required only if not communicated by the International Bureau).
 - b. ☒ has been communicated by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☐ An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)).
 - a. ☐ is attached hereto.
 - b. ☐ has been previously submitted under 35 U.S.C. 154(d)(4).
7. ☐ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3))
 - a. ☐ are attached hereto (required only if not communicated by the International Bureau).
 - b. ☐ have been communicated by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☐ have not been made and will not be made.
8. ☐ An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. ☐ An oath or declaration of the inventor(s) (35 U.S.C. 371 (c)(4)).
10. ☐ An English language translation of the annexes of the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)).
11. ☒ A copy of the International Preliminary Examination Report (PCT/IPEA/409).
12. ☒ A copy of the International Search Report (PCT/ISA/210).

Items 13 to 20 below concern document(s) or information included:

13. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
14. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
15. ☒ A **FIRST** preliminary amendment.
16. ☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
17. ☐ A substitute specification.
18. ☐ A change of power of attorney and/or address letter.
19. ☐ A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821 - 1.825.
20. ☐ A second copy of the published international application under 35 U.S.C. 154(d)(4).
21. ☐ A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4).
22. ☒ Certificate of Mailing by Express Mail
23. ☐ Other items or information:

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR

INTERNATIONAL APPLICATION NO.

ATTORNEY'S DOCKET NUMBER

PCT/GB/00/00191

65008-031

24. The following fees are submitted:

BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)) :

- ☐ Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO \$1000.00
- ☒ International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO \$860.00
- ☐ International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO \$710.00
- ☐ International preliminary examination fee (37 CFR 1.482) paid to USPTO but all claims did not satisfy provisions of PCT Article 33(1)-(4) \$690.00
- ☐ International preliminary examination fee (37 CFR 1.482) paid to USPTO and all claims satisfied provisions of PCT Article 33(1)-(4) \$100.00

ENTER APPROPRIATE BASIC FEE AMOUNT =

\$860.00

Surcharge of \$130.00 for furnishing the oath or declaration later than ☐ 20 ☐ 30 months from the earliest claimed priority date (37 CFR 1.492 (e)).

\$0.00

| CLAIMS | NUMBER FILED | NUMBER EXTRA | RATE | |
|--------------------------------------------------|--------------|--------------|--------------------------|---------|
| Total claims | 15 - 20 = | 0 | x \$18.00 | \$0.00 |
| Independent claims | 4 - 3 = | 1 | x \$80.00 | \$80.00 |
| Multiple Dependent Claims (check if applicable). | | | <input type="checkbox"/> | \$0.00 |

TOTAL OF ABOVE CALCULATIONS = \$940.00

- ☐ Applicant claims small entity status. (See 37 CFR 1.27). The fees indicated above are reduced by 1/2.

\$0.00

SUBTOTAL = \$940.00

Processing fee of \$130.00 for furnishing the English translation later than ☐ 20 ☐ 30 months from the earliest claimed priority date (37 CFR 1.492 (f)).

\$0.00

TOTAL NATIONAL FEE = \$940.00

Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31) (check if applicable).

\$0.00

TOTAL FEES ENCLOSED = \$940.00

| | |
|-----------------------|----|
| Amount to be refunded | \$ |
| charged | \$ |

- a. ☒ A check in the amount of \$1,080.00 to cover the above fees is enclosed.
- b. ☐ Please charge my Deposit Account No. _____ in the amount of _____ to cover the above fees. A duplicate copy of this sheet is enclosed.
- c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 08-2789. A duplicate copy of this sheet is enclosed.
- d. ☐ Fees are to be charged to a credit card. **WARNING:** Information on this form may become public. **Credit card information should not be included on this form.** Provide credit card information and authorization on PTO-2038.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and submitted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:

Harold W. Milton
HOWARD & HOWARD ATTORNEYS, P.C.
 39400 Woodward Avenue - Suite 101
 Bloomfield Hills, MI 48304

Telephone: 248-645-1483
 Facsimile: 248-645-1568

SIGNATURE

Harold W. Milton

NAME

22,180

REGISTRATION NUMBER

26 JULY 2001

DATE

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant : 3-D COMPOSITES LIMITED et al. :
:
Serial No. : Not Yet Assigned :
:
Attny No. : 65,008-031 : **GROUP:**
:
Filed : Concurrently Herewith :
:
Title : CONSTRUCTION SYSTEM :
:

PRELIMINARY AMENDMENT

Assistant Commissioner of Patents
Washington, D. C. 20231

Dear Sir:

Please preliminary amend the above-identified application as follows:

IN THE CLAIMS

Please preliminary amend the following claims as follows:

Claim 1 has been amended as follows:

1. (Amended) A method of building which comprises taking honeycomb panels having at least one flat edge for bonding to an adjacent structural unit, and bonding the panels and/or units together to form a composite building structure.

Claim 3 has been amended as follows:

3. (Amended) A method as claimed in claim 2 in which the honeycomb configuration is obtained by injecting a plastics material resin into a continuous web of fibres laid within a mould in such a fashion that a honeycomb structure is produced without the web crossing itself.

Claim 4 has been amended as follows:

4. (Amended) A method as claimed in any of claim 3 in which the construction of the panel is such that the honeycomb format is always integrated into and bounded by a continuous straight edge.

Claim 6 has been amended as follows:

6. (Amended) A method as claimed in any of claim 5 wherein the third element, that of corners, is provided by the use of a box section.

Claim 7 has been amended as follows:

7. (Amended) A method as claimed in any of claim 6 wherein the honeycomb panel is preferably bounded on all four sides by flat edges and can therefore be fastened to other panels or beam sections or a combination of both.

Claim 8 has been amended as follows:

8. (Amended) A method as claimed in any claim 7 wherein the honeycomb panel is made as an open structure for use in for example a cavity wall, and a facing board bonded directly onto it in situ.

Claim 11 has been amended as follows:

11. (Amended) A method as claimed in claim 10 wherein the panels and other units are made from a thermoplastic resin and heating elements provided to fuse adjacent abutting surfaces, together by localised melting of the material.

REMARKS

Claims 1-15 remain in this application. The entrance of this preliminary amendment for the purposes of clarifying the specification is respectfully requested.

Respectfully submitted

HOWARD & HOWARD ATTORNEYS, P.C.

7/26/01
Date


Harold W. Milton, Registration No. 22,180
The Pinehurst Office Center, Suite #101
39400 Woodward Avenue
Bloomfield Hills, Michigan 48304-5151
(248) 723-0352

HWM/alw
G:\T-V\Urquhart\p00031\Patent\Preliminary Amendment.doc

VERSION WITH MARKS TO SHOW CHANGES MADE

IN THE CLAIMS

Please amend the claims as follows:

Please amend Claim 1 as follows:

1. (Amended) A method of building which comprises taking honeycomb panels
[~~(as hereinbefore defined)~~] having at least one flat edge for bonding to an adjacent structural unit,
and bonding the panels and/or units together to form a composite building structure.

Please amend Claim 3 as follows:

3. (Amended) A method as claimed in claim [~~1- or~~] 2 in which the honeycomb
configuration is obtained by injecting a plastics material resin into a continuous web of fibres laid
within a mould in such a fashion that a honeycomb structure is produced without the web
crossing itself.

Please amend Claim 4 as follows:

4. (Amended) A method as claimed in any of claim[s-~~1- to~~] 3 in which the
construction of the panel is such that the honeycomb format is always integrated into and
bounded by a continuous straight edge.

Please amend Claim 6 as follows:

6. (Amended) A method as claimed in any of claim[s-~~1- to~~] 5 wherein the third
element, that of corners, is provided by the use of a box section.

Please amend Claim 7 as follows:

7. (Amended) A method as claimed in any of claim[s-1-to] 6 wherein the honeycomb panel is preferably bounded on all four sides by flat edges and can therefore be fastened to other panels or beam sections or a combination of both.

Please amend Claim 8 as follows:

8. (Amended) A method as claimed in any claim[s-1-to] 7 wherein the honeycomb panel is made as an open structure for use in for example a cavity wall, and a facing board bonded directly onto it in situ.

Please amend Claim 11 as follows:

11. (Amended) A method [~~according to any preceding claim~~] as claimed in claim 10 wherein the panels and other units are made from a thermoplastic resin and heating elements provided to fuse adjacent abutting surfaces, together by localised melting of the material.

CONSTRUCTION SYSTEM

This invention relates to a construction system and in particular relates a construction system using composite materials.

Advanced composite materials have physical properties which make them ideal materials for the building of many types of constructions, particularly houses. They are light weight, typically less than 25% the weight of steel, and yet comparable to steel in strength. As processed they can withstand permanent immersion in water and are not attacked by various types of rot or eaten by termites. If effectively constructed into a house or other building they offer the possibility of structures capable of withstanding earthquakes and hurricanes. If the fibre used in the composite is glass fibre, then the raw material is both abundant and cheap and the glass can be recycled. Composites have excellent creep resistance making them suitable for load application over long periods of time. Thermal properties are excellent offering the possibility of reduced energy demand thus allowing renewable energy sources, such as solar energy, to become a significant source of heating.

Although advanced composites have slowly found new applications, their use in large complex structures such as buildings and houses has been almost non-existent to date. Composite structural elements such as beam sections, for example "I" beams, angle sections, and box beams, have been manufactured by the "pultrusion" process for many years, but have proved difficult to fasten together. Composites do not plastically deform like metals and therefore cannot be as effectively fastened together using bolts, screws or rivets. Furthermore they cannot be welded. The lack of effective fastening methods has severely restricted growth in the use of advanced composites despite their excellent physical properties.

The object of this invention is to provide a system of composite structural elements and methods of construction that effectively fuse the structural elements into a single complex

- 2 -

advanced composite structure, suitable for many applications but particularly suitable for the construction of houses or other buildings.

In its broadest aspect the present invention provides a method of building which comprises taking honeycomb panels (as hereinafter defined) having at least one flat edge for bonding to an adjacent structural unit, and bonding the panels and/or units together to form a composite building structure.

The adjacent structural unit may be another honeycomb panel, or a beam, corner, or other desired unit as will be described more fully hereinafter.

An analysis of a typical wall, as shown in figure 1 of the accompanying drawings, shows that any structure of this type contains three fundamental elements, panels, beams and corners. Any construction system must therefore effectively provide these elements.

Manufacturing large composite panels using conventional sections is difficult as flat sheets of material are not sufficiently rigid and a lot of additional support structure must be added to achieve the desired rigidity of a wall panel. This problem is overcome by the honeycomb panel of our European patent number 0 708 706. The honeycomb configuration of this structure makes it an ideal panel and it can be manufactured in an open or faced panel format. Furthermore it can be made in large sizes for example 0.9m x 2.5m and 40mm thick. The panel can be modularised by constructing the fibre reinforcement into a narrow width panel preform, say 300mm wide. At the moulding stage three fibre preforms can be loaded into an appropriate mould tool and a panel made of 900mm width. A further property of the panel is that it acts like a beam in all directions, but is particularly effective as a beam when loaded on its edge as illustrated in figure 2 of the accompanying drawings. The construction of the panel may be such that the honeycomb format is always integrated into and bounded by a continuous straight edge. By effectively fastening a composite beam section such as a flat plate or box section to the edges of the panel, the properties of the panel, functioning as a beam, can be so enhanced as to make it effectively a beam, as illustrated in figures 3 and 4 of the accompanying drawings.

- 3 -

The honeycomb panel therefore provides two elements of the wall, namely the panel and the beam. The third element, that of corners, can be solved by the use of a box section. A box section by definition has a number of faces, typically four, but can be three or more than four. In figure 4 of the accompanying drawings three panels are shown attached to a single four sided box beam.

The box beam therefore acts as a corner allowing the panels in effect to change direction e.g. by 90°.

The honeycomb panel is preferably bounded on all four sides by flat edges and can therefore be fastened to other panels or beam sections or a combination of both. Hence by combining these elements the construction of complex structures is possible and the requirement for panels, beams and corners is fulfilled.

A property of the honeycomb panel is that it can be made as an open structure and an alternative construction method would be, in for example a cavity wall, for the inner panel to be of open structure and a facing board bonded directly onto it in situ. The facing board could be plasterboard, fabric covered board, or any desired decorative or fastened surface.

It has been demonstrated that by a combination of honeycomb panels and beam sections complex structures can be created, however a method of effectively fastening these elements together is required and the resultant structure must be examined to determine if additional structure in the form of brackets is required.

An advantage of composites is that they can be very effectively bonded by modern adhesives to the extent that the joint becomes as strong as the base material. Furthermore the honeycomb panel is preferably always bounded by a flat face which can mate with a flat face of another panel or a beam section. There therefore exists an opportunity to create a bonded joint at the interface of these flat surfaces.

A correctly constructed joint would in effect "weld" the elements of the system together allowing them to function as a single element. Such a joint would also be water-tight.

- 4 -

According to a second aspect of the present invention there is provided a method of joining adjacent structural units which comprises providing an abutting edge of an end unit with a slightly recessed area capable of receiving adhesive extending across less than the width of the edge, and at least one more greatly recessed area capable, either alone or in combination with the corresponding area of the abutting unit, of forming a gallery for rapid transit of adhesive along substantially the entire abutting surfaces.

In a preferred embodiment of the second aspect of the invention, one or both abutting surfaces may be provided with heating elements to achieve rapid cure, even in cold conditions.

According to a third embodiment of the invention, the panels and other units may be made from a thermoplastic resin and heating elements provided to fuse adjacent abutting surfaces together by localised melting of the material.

According to a fourth embodiment of the invention there is provided a method of making a cavity wall which comprises taking two or more honeycomb panels and locating them in spaced apart relationship by means of a recess or raised area in a unit abutting at least one edge of the panel and bonding the panels to the unit.

In the construction of buildings and in particular houses it is an advantage if the walls can be of a cavity construction. The cavity offers the facility to add insulation and run services such as electricity wires, telephone wires and pipe work within the wall thus hidden from view. Using the honeycomb panel with faced surfaces and by arranging the faced surfaces to face to the outside, a cavity wall can be created. The unit may be a corner and is preferably recessed to locate the panels.

A fifth embodiment of the invention provides a method of forming a casement for a window, door or the like, in a cavity wall according to the fourth embodiment, comprises forming a hole of the desired size whether by omitting a panel or cutting an existing panel, and sealing and retaining the edges of the hole by applying a shaped strip which grips the panels, and bonding the strip in place.

- 5 -

In the case of a single leaf wall, a simpler strip may be employed which encapsulates the edge of the (single) panel.

According to a sixth embodiment of the invention there is provided a ferrule for sealing a beam to a beam or other unit which comprises a block of material shaped to fit partly within a beam end where it can be bonded, having an end surface capable of being bonded to a flat surface of a beam or other unit.

The invention will be described further, by way of example, with reference to the accompanying drawings, in which:

Figure 1 is a diagrammatic perspective view of two walls of a building;

Figure 2 illustrates the honeycomb panel or a beam;

Figures 3 & 3a expand on figure 2;

Figure 4 shows panels attached to a square beam;

Figures 5, 5a & 6 illustrate a cavity wall according the invention;

Figures 7 & 8 illustrate the method of joining in accordance with the invention;

Figures 9 & 10 illustrate the welding of thermoplastic units;

Figures 11 to 15 illustrate the joining of beams; and

Figures 16a, b & c illustrate the formation of casements for windows and the like.

Referring to three drawings, figure 1 illustrates the beam 10, panels 12 and corners 14 required in any building system.

-6-

Figures 2, 3 and 3a show a honeycomb panel 12 in accordance with EP-A-0708706 acting as a beam and indeed being formed into I-beams by the bonding thereto of flat members 16 (which can themselves be honeycomb panels).

Figure 4 shows a square corner 14 having three panels 12 attached thereto.

Figures 5 and 6 illustrate the cavity wall of the invention in which two panels 12 are held in spaced apart relationship by a beam 18 having a raised area 20 which locates and supports the panels. The panels are then bonded to the beam 18 to form the wall. There may be beams 18 on all four sides of the wall thereby sealing it, or other units may be used. In figure 6 the honeycomb structure 22 can be seen where a facing panel 24 is cut away. The panel 24 can be omitted on the insides of the wall, and inner and outer panels may be, and indeed are likely to be, different from one another as one may need to be weather resistant and the other carrying a decorative finish, for example. In the construction of figure 5a, 'I'-beam spacers 25 are employed, preferably bonded to the respective inner faces of the panels 12. The spacers 25 may be of composite material or of other suitable material such as aluminium. The spacers lock the respective faces together and greatly increase the strength of the wall. This construction may be employed for very high stress-bearing wall, e.g. those carrying kitchen units or cupboards, or for buildings in areas exposed to hurricanes.

The honeycomb panels and beam sections are preferably a composite of, typically, glass fibres and acrylic based resin. At the interface of a panel and beam a joint 26 is formed as shown in figure 7. Half of the joint 26 is provided in each element being bonded and consists of a glue line 28, two sealed edges 30 and a gallery 32. At suitable locations along this joint, vent holes and injection holes are provided as necessary. The joint 26 is made as follows. The panels and beam elements are assembled and temporarily held in their respective locations in a fixture or with clamps and simultaneously all joint edges are sealed.

An adhesive, for example of the type supplied by Permabond and designated 5002, also an acrylic based resin, is injected under pressure directly into the gallery 32 of the joint 26.

- 7 -

The resin is then distributed into the glue line 28 from the gallery 32 and air is expelled through the vents. On completion of the injection, signified by resin appearance at the vents, both vents and the hole for the nozzle are plugged off with small plastic plugs. This type of adhesive will cure sufficiently, at 20°C, within 15 minutes to a point where the structure will be self supporting and can be removed from a fixture or clamps removed as appropriate. The glue line 28 is continuous around the contact surfaces and because it has been filled by adhesive under pressure, the joint will be completely water tight. Hence structures which are required to hold water or repel water such as roof structures can be produced. The joint edges 30 are sealed by placing a gasket material on the appropriate edge prior to assembly. Companies such as Permabond & Loctite supply a wide range of suitable material.

If assembly is occurring at low temperatures, resistance type heating elements 34, which in reality are very thin wires, can be incorporated into the face of the glue line of the panel (fig 8). These can be activated at the time of injection and for a short period after to ensure a full cure of the adhesive.

Although the composite described, consists of glass fibres and a thermosetting resin, advances in plastic materials and development of new fibres might make it possible to reproduce the elements of the construction system with sufficient mechanical strength as to make them a viable proposition using thermoplastic material. Thermoplastics are, however, difficult to bond with adhesives and the joint described would not work. Alternative joints will now be described which allow the structural elements to be welded.

In the first instance heating elements 34 are moulded into or bonded onto the jointing face of the honeycomb panel (or the beam), as shown in figure 9. The elements are then heated by passing an electric current through them and as the contact face melts the panels and beams sections are compressed together effectively welding them together. This method is capable of producing an excellent joint but requires movement of the components. A second joint which allows fixed clamping will now be described.

-8-

Again heating elements 34 are provided in the joining face of the honeycomb panel 12. In addition, in the centre of the joint, a groove 36 is provided into which a plastic strip 38 is located, (fig 10). The plastic strip contains a heat activated foaming agent which when heated expands. As the joint is heated by the elements and becomes liquid the expanding plastic strip pressurises the liquid forcing it in contact with the face of the mating component thus causing a good welded joint. The heating elements 34 are positioned so as not to melt the extreme edges of the panel thus allowing the edges to retain the melted plastic within the joint. Joints of the type described could be made in less than 5 minutes and would provide a very rapid assembly method.

Referring now to figures 11 to 15, the joining of beams is considered. In situations where a box section butts up to the side of a beam and honeycomb panels 12 are bonded to both beams (fig 13), the panel 12 acts itself as a corner bracket and no additional bracket is required. If, however, due to structural or sealing considerations an additional bracket is required, this can be achieved by a ferrule plug bracket (fig 14) which works as follows. A bracket 40 is moulded from a similar composite to the other structural elements and is bonded to the end of the beam section 10 which forms the butt joint as shown in figure 14. The beams and honeycomb panels are then assembled and at the same time the ferrule plug bracket 40 is bonded onto the adjoining beam, a suitable adhesive again being Permabond 5002. This type of bracket seals the butt joint of beam to beam, strengthens the open end of the beam and makes use of the large available surface area within the beam to achieve a very strong joint. Externally the bracket and beam appear as a continuation of the beam and the joint continuity between beams and honeycomb panels is maintained. The area 42 is spread with adhesive and bonded to the inside of the beam 10 while the area 44 is spread with adhesive and bonded to the external surface of corner 14.

In situations where a beam has to be joined to another length of beam a joint 46 can be made using a short length of beam which just slides inside the larger main beam, (fig 15). The joint is bonded into place in one of the two beams and then the second beam is slid over the projecting portion of the joint and bonded in place to form a butt joint. Connecting honeycomb panels to the beam such that they overlap the joint further strengthens the join. A suitable adhesive would again be Permabond 5002.

In situations where simple brackets such as angle brackets are required, these can be bonded, or bonded and screwed, to the composite structure. Aluminium can also very effectively be bonded to the composite particularly with acrylic adhesives of the type Permabond 5002. Aluminium beam sections could be used in place of the composite beams and there are potential applications for this substitution.

The composite structure so far described has not addressed how to create openings for doors and windows. In figure 16a a cavity wall is shown with partial window opening together with a shaped strip section 50 providing the casement for a window. The shaped strip has the profile illustrated in figure 16c and as can be seen comprises two recesses 52 which grip the respective leaves 12 of the cavity wall, separated by a spacer section 54 to separate the panels 12. The construction of the inner facing surface of the strip 50 is determined by the window or the like to be fitted into the casement opening. The assembly procedure would involve clamping all the elements together and injecting adhesive into a glue line created in the honeycomb panel and shaped strip (similar to that described hereinabove). The ends of the shaped strip section are pre-bonded on assembly thus sealing the glue line.

Now if a window or door aperture is cut out of the honeycomb panel, which is possible using conventional routing equipment and diamond cutters, the exposed edges of the honeycomb would be present and no glue line joint is available (fig 16b). By using the same shaped strip it is possible by applying adhesive to all the surfaces in contact with the section to achieve an excellent joint, even though this is not continuous. The strip is so designed as to encapsulate each panel thus tying the two panels together and retaining a high degree of structural integrity. Window and door frames can be directly attached to the casement opening so made.

Although the panels of the invention have been described with respect to walls, it will be appreciated that they can be used in any building or construction end-use, e.g. floor panels, roofing panels, or the like.

-10-

The invention provides a construction system capable of using largely factory pre-formed parts and quickly and cheaply erecting a building which is immensely strong, being effectively of an integral monocoque construction, as well as being rot- and insect- proof.

CLAIMS

1. A method of building which comprises taking honeycomb panels (as hereinbefore defined) having at least one flat edge for bonding to an adjacent structural unit, and bonding the panels and/or units together to form a composite building structure.
2. A method as claimed in claim 1 wherein the adjacent structural unit is another honeycomb panel, or a beam, or corner.
3. A method as claimed in claim 1 or 2 in which the honeycomb configuration is obtained by injecting a plastics material resin into a continuous web of fibres laid within a mould in such a fashion that a honeycomb structure is produced without the web crossing itself.
4. A method as claimed in any of claims 1 to 3 in which the construction of the panel is such that the honeycomb format is always integrated into and bounded by a continuous straight edge.
5. A method as claimed in claim 4 wherein the panel is enhanced to make it a beam by effectively fastening a composite beam section such as a flat plate or box section to the edges of the panel.
6. A method as claimed in any of claims 1 to 5 wherein the third element, that of corners, is provided by the use of a box section.
7. A method as claimed in any of claims 1 to 6 wherein the honeycomb panel is preferably bounded on all four sides by flat edges and can therefore be fastened to other panels or beam sections or a combination of both.
8. A method as claimed in any claims 1 to 7 wherein the honeycomb panel is made as an open structure for use in for example a cavity wall, and a facing board bonded directly onto it in situ.

-12-

9. A method of joining adjacent structural units which comprises providing an abutting edge of an end unit with a slightly recessed area capable of receiving adhesive extending across less than the width of the edge, and at least one more greatly recessed area capable, either alone or in combination with the corresponding area of the abutting unit, of forming a gallery for rapid transit of adhesive along substantially the entire abutting surfaces.

10. A method as claimed in claim 9 wherein one or both abutting surfaces is provided with heating elements to achieve rapid cure, even in cold conditions.

11. A method according to any preceding claim wherein the panels and other units are made from a thermoplastic resin and heating elements provided to fuse adjacent abutting surfaces, together by localised melting of the material.


12. A method of making a cavity wall which comprises taking two or more honeycomb panels and locating them in spaced apart relationship by means of a recess or raised area in a unit abutting at least one edge of the panel and bonding the panels to the unit.




13. A method of forming a casement for a window, door or the like, in a cavity wall according to claim 12 comprises forming a hole of the desired size whether by omitting a panel or cutting an existing panel, and sealing and retaining the edges of the hole by applying a shaped strip which grips the panels, and bonding the strip in place.

14. A method according to claim 13 wherein, in the case of a single leaf wall, a simpler strip may be employed which encapsulates the edge of the (single) panel.


15. A ferrule for sealing a beam to a beam or other unit which comprises a block of material shaped to fit partly within a beam end where it can be bonded, having an end surface capable of being bonded to a flat surface of a beam or other unit.

-1/13-


FIG. 1

FIG. 2FIG. 3FIG. 3a



-3/13-

FIG. 4



-4/13-

FIG. 5a



-5/13-





-6/13-

FIG. 7FIG. 8


-7/13-

FIG. 9FIG. 10


-8/13-

FIG. 11FIG. 12


-9/13-

FIG. 13

-10/13-

FIG. 14

-11/13-



-12/13-






FIG. 16a

-13/13-

FIG. 16bFIG. 16c

Docket No.
65,008-031

Declaration and Power of Attorney For Patent Application

English Language Declaration

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name,

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

CONSTRUCTION SYSTEM

the specification of which

(check one)

☐ is attached hereto.

☒ was filed on July 26, 2001 as United States Application No. or PCT International Application Number 09/890,091 and was amended on _____

(if applicable)

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose to the United States Patent and Trademark Office all information known to me to be material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56.

I hereby claim foreign priority benefits under Title 35, United States Code, Section 119(a)-(d) or Section 365(b) of any foreign application(s) for patent or inventor's certificate, or Section 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate or PCT International application having a filing date before that of the application on which priority is claimed.

Prior Foreign Application(s)

Priority Not Claimed

GB00/00191
(Number)
99016222

PCT
(Country)
GB

24/01/2000
(Day/Month/Year Filed)
26/01/1999

☐

(Number)

(Country)

(Day/Month/Year Filed)

☐

(Number)

(Country)

(Day/Month/Year Filed)

☐

I hereby claim the benefit under 35 U.S.C. Section 119(e) of any United States provisional application(s) listed below:

(Application Serial No.)

(Filing Date)

(Application Serial No.)

(Filing Date)

(Application Serial No.)

(Filing Date)

I hereby claim the benefit under 35 U. S. C. Section 120 of any United States application(s), or Section 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of 35 U.S.C. Section 112, I acknowledge the duty to disclose to the United States Patent and Trademark Office all information known to me to be material to patentability as defined in Title 37, C. F. R., Section 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application:

(Application Serial No.)

(Filing Date)

(Status)
(patented, pending, abandoned)

(Application Serial No.)

(Filing Date)

(Status)
(patented, pending, abandoned)

(Application Serial No.)

(Filing Date)

(Status)
(patented, pending, abandoned)

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith. (list name and registration number)

| | | | |
|-----------------------|---------------------|----------------------|-------------------|
| Gregory D. DeGrazia | P-48,944 | Jeffrey A. Sadowski | 29,005 |
| Samuel J. Haidle | 42,619 | Raymond E. Scott | 22,981 |
| William H. Honaker | 31,623 | Randall L. Shoemaker | 43,118 |
| David M. LaPrairie | 46,295 | Steve C. Wichmann | 37,758 |
| Harold W. Milton, Jr. | 22,180 | James R. Yee | 34,460 |

Send Correspondence to:

Harold W. Milton, Jr.
HOWARD & HOWARD ATTORNEYS, P.C.
The Pinehurst Office Center, Suite #101
39400 Woodward Avenue
Bloomfield Hills, Michigan 48304-5151

Direct Telephone Calls to: (name and telephone number)

Harold W. Milton (248) 723-0352

| | | | |
|-----------------------------------------------------|--|---------------|--|
| Full name of sole or first inventor | | July 26, 2001 | |
| John Reginald Newton | | Date | |
| Sole or first inventor's signature | | | |
| <i>John R. Newton</i> | | | |
| Residence | | | |
| 3 Lumley Road, Kendal Cumbria LA9 5HT Great Britain | | | |
| Citizenship | | | |
| United Kingdom GBN | | | |
| Post Office Address | | | |
| 3 Lumley Road | | | |
| Kendal, Cumbria LA9 5HT Great Britain | | | |

| | |
|--------------------------------------|--|
| Full name of second inventor, if any | |
| Second inventor's signature | |
| Date | |
| Residence | |
| Citizenship | |
| Post Office Address | |
| | |
| | |